

balcıođlu grup
standart
İZOLASYON MATERYALLERİ

Product Catalogue

Factory Address: FEVZIPASA MAH. KINALI KAVSAGI CAD. NO: 123 SILIVRI / ISTANBUL

Head Office Address: İKİTELLİ OSB KERESTECİLER SİTESİ 4.BLOK NO: 43 BASAKSEHIR / ISTANBUL

Phone: +90 (212) 670 49 51 (pbx) - **Fax :** +90 (212) 670 51 51
export@standartinsulation.com - www.standartinsulation.com



ENGLISH

CERTIFICATES

Quality of
Standart,
Standard of the
Quality..



SIM BITUMINOUS MEMBRANES

SIM Penguen Series



Penguen Series waterproofing membranes are plastomeric bituminous waterproofing sheets that are ideal for cold, hot and mild climate zones. Atactic Polypropylene (A.P.P.) with thermoplastic resin is used in this type of membranes to enhance durability of the bitumen. The fiberglass and polyester reinforcements inside the membranes provide a higher resistance against tensions by enhancing the mechanical resistance. Penguen series membranes are very commonly used in many markets. Membranes with a 1 meter width are produced at 10 meters length. Only the membranes of 2 mm thickness are produced at 1 meter width and at 15 meters length.

Areas of usage

While bituminous membranes are used anywhere water can leak into such as; walls in contact with soil, foundations, floorings that fit on the ground, they can be used at places the water can pond or wet areas below water level such as; external walls, balconies, terraces, sloped roofs,

bathrooms, kitchens, toilets.

In addition, Penguen bituminous waterproofing sheets are used in water tanks, pools, safety walls and ,depending on the characteristics of the surface, in artificial lakes and concrete canals. Penguen waterproofing sheets brings economic and aesthetic solutions many more issues..

FEATURES


- Provides a strong hold of the surface and great adhesion. Retains this quality after the application too. Especially, in foundation curtain wall insulation this feature is more clearly visible. Can be applied on different surfaces like wood and concrete.

- Demonstrates more than enough flexibility against structural movements with its longitudinal and transverse tensile strength. Durable against movements and dilatation.

- Neither melting in hot weather nor breaking or cracking in cold weather. Our membranes are easily applied using torch fire. With proper cutting equipment, they can be cut as needed.

- Demonstrates perfect compliance to dilatations, concrete gutters, parapet turns and chimney flashings. When used as instructed and under sufficient protection, gives lifelong insulation to the building.

Cold Flexibility : -5 °C
Heat resistance : 110 °C



SIM Panda Series



Panda Series waterproofing membranes are plastomeric waterproofing membranes, the ideal choice in continental climate (cold and hot). The fiberglass and polyester reinforcements inside the product give the bitumen a better durability. To enhance the physical resistance of the membranes, fiberglass or polyester mat is used as reinforcement.

Areas of usage


While bituminous membranes are used anywhere water can leak into such as; walls in contact with soil, foundations, floorings that fit on the ground, they can be used at places the water can pond or wet areas below water level such as; external walls, balconies, terraces, sloped roofs, bathrooms, kitchens, toilets.

In addition, Panda bituminous waterproofing sheets are used in water tanks, different types of pools, safety walls, concrete canals, parking areas and at places under heavy tension such as roadways, railroad transportation systems, bridges and viaducts.

FEATURES

- Waterproofing membranes with diverse areas of use due to great performance in different climates. With its impermeability, provides certain waterproofing.
- Provides a strong hold of the surface and great adhesion. Retains this quality after the application too. Especially, in foundation curtain wall insulation this feature is more clearly visible. Can be applied on different surfaces like wood and concrete.
- Demonstrates more than enough Flexibility against structural movements with its longitudinal and transverse tensile strength. Durable against movements and dilatation.
- Neither melting in hot weather nor breaking or cracking in cold weather. Our membranes are easily applied using torch fire. With proper cutting equipment, they can be cut as needed.
- Demonstrates perfect compliance to dilatation, concrete gutters, parapet turns and chimney flashing. When used as instructed and under sufficient protection, gives lifelong insulation to the building.

Cold Flexibility : -10 °C
Heat resistance : 120 °C



SIM Fok Series




Fok Series waterproofing membranes are elastomeric bituminous waterproofing sheets that are ideal for especially cold climate zones. This type of bituminous membranes are enriched with Styrene – Butadiene – Styrene (SBS) with thermo plastic resin, to enhance the durability of the bitumen. The fiberglass and polyester reinforcements inside the membranes provide a higher resistance against tensions by enhancing the mechanical resistance. Membranes with a 1 meter width are produced at 10 meters length. Only the membranes of 2 mm thickness are produced at 1 meter width and at 15 meters length.

Areas of usage

FOK series bituminous waterproofing sheets are elastomeric (SBS) based. They contain polyester mat or fiberglass reinforcement to enhance tension resistance.

Fok Series, the ideal choice in cold climates are used on walls in touch with soil, foundations or floorings that fit on the ground. As well as these,



they can be used at places the water can pond or wet areas below water level such as; external walls, balconies, terraces, sloped roofs, bathrooms, kitchens, toilets, water tanks, pools, safety walls and ,depending on the characteristics of the surface, in artificial lakes and concrete canals.

Especially, because its flexible structure can endure dilatations or shrinking, in moving structures, deep foundations and metal roofs FOK is frequently preferred.

FEATURES

- Under conditions where the temperature is below freezing point, FOK series products do not lose their performance and retain their Flexibility. They demonstrate more than enough Flexibility against structural movements with its longitudinal and transverse tensile strength.

- FOK series membranes are suitable for hot asphalt application too.

- Provides a strong hold of the surface and great adhesion. Retains this quality after the application too. Especially, in foundation curtain wall insulation this feature is more clearly visible. Can be applied on different surfaces like wood and concrete.

- Resistant against structural movements and dilatation. With its quite flexible structure, it is preferred in metal roofs which always have a tendency to dilate and bend.

- Neither melting in hot weather nor breaking or cracking in cold weather. Our membranes are easily applied using torch fire. With proper cutting equipment, they can be cut as needed.

- Demonstrates perfect compliance to dilatation, concrete gutters, parapet turns and chimney flashing. When used as instructed and under sufficient protection, gives lifelong insulation to the building.

Cold Flexibility : -20 °C
Heat resistance : 100 °C



PRINCO Series



Princo Series waterproofing membranes are plastomeric bituminous waterproofing sheets that are ideal for cold and mild climate zones. Atactic Polypropylene (A.P.P.) with thermoplastic resin is used in this type of membranes to enhance durability of the bitumen. The fiberglass and polyester reinforcements inside the membranes provide resistance against tensions by enhancing the mechanical resistance. Princo series membranes are very commonly used in many markets. Membranes with a 1 meter width are produced at 10 meters length.




Areas of usage

While bituminous membranes are used anywhere water can leak, they can be used at places the water can pond or wet areas below water level such as; external walls, balconies, terraces, sloped roofs, bathrooms, kitchens, toilets. Not appropriate for use on green roofs. Not used as surface layer or single ply.

RECOMMENDATIONS:

1. Application surface must be smooth, free of moisture, ponding water and dust.
2. The application area must be provided with an adequate drainage system.
3. The substrate must be primed with a bituminous based product (Standart PRIMER) and allowed to dry prior to application. At least 400 g/m2 of application is advised. For utmost results, 800 g/m2 is recommended.
4. Do not apply below +5 °C.
5. Do not apply under adverse weather conditions.
6. In case of application on vertical or considerable slopes, apply proper mechanical fasteners.
7. See our website (www.standartinsulation.com or youtube channel) for application details and supporting visuals.

Cold Flexibility : -10 °C
Heat resistance : 110 °C



SIM Mineral Surface Membrane



FEATURES

- Red, Green, Grey and White are color options.
- Used on the last upper layer, the product demonstrates technical and aesthetical insulation solutions.
- UV resistant thanks to the mineral coating.
- Does not require additional protective concrete.
- Demonstrates perpetuity.
- Practical, applied very fast and easily with Torch fire. Long lasting and economic.
- Durable against structural movements and dilatation.
- Complies with every climate thanks to wide range of products.
- Environment friendly, does not harm the nature or living beings.
- Demonstrates perfect watertightness with its impermeability.
- Provides a strong hold of the surface and great adhesion.
- With dedicated cutting equipment, they can be cut as needed.
- Demonstrates perfect compliance to dilatation, concrete gutters, parapet turns and chimney flashing


Standart reflective mineral coated bituminous sheets are a common solution to many waterproofing problems with their precise impermeability and wide areas of application. This type of bituminous membranes have a reflective mineral coated upper surface while the lower surface is covered with Polyethylene film.

Fiberglass or Polyester mat is used in mineral coated bituminous membranes produced either Plastomeric (A.P.P. Modified) or Elastomeric (S.B.S. Modified). Mineral coated membranes are produced at 1 meter width and 10 meters length.

COLORS



Custom colors available on demand.



SIM Membrane Application Images



SIM Quickshingle



Four season: It can be applied at any sloping roof and in any season.

FEATURES



- Economic price and low labor cost
- Easy application, even by end user
- Monolithic pattern and its self adhesive features prevents tearing caused by wind
- Strong and reliable
- Monolithic pattern prevents dust and dirt because of its flat surface in contrast to leaf type shingles.
- Adds value to buildings with changing the view of the building.





Quick Shingle was created to be used in place of any kind of roofing material. It is a granule stone coated bituminous membrane roofing material with surface of painting or formed theme, pattern (tile image, etc.) figure, image, logo and / or print. Quick shingle has been produced as an alternative roofing material for terrace and sloping roofs.

WHY SHOULD I USE QUICKSHINGLE?

- Low labor cost.
- A workman lays 30-50m² shingles, 20-30m² tiles but 80-100m² quick shingle in one shift. Low wastage and light weight compared to other types. It can be applied by end users because of its easy application.
- Weight: 3 times lighter than its competitors.
- Nonfading: Stays colored for long years thanks to its UV protecting pigments.
- Leak proof: Full leak proofing and insulation because of Torch application and no nails.

TECHNICAL SPECIFICATIONS		
SPECIFICATION	VALUE	UNIT
Length	10	m
Width	1	m
Thickness	3,5	mm
Weight	>40	KG / Roll
Water Tightness	10 kPa	kPa
Flexibility at low temperature	-5	°C
Tensile Strength (Width)	400	N/50mm
Tensile Strength (Length)	600	N/50mm
Elongation at Break (Width)	30	%
Elongation at Break (Length)	30	%
Flow resistance at elevated temperatures	110	°C
Behaviour to Fire	E	-
Hazardous material	N/A	-
External Fire Performance	Broof	





simAlfo Membrane



Aluminium coated bituminous sheets used as the uppermost layer are applied practically using torch fire. Presents aesthetic and economic ways in insulation. Resistant to UV rays and heavy weather conditions.

Areas of usage

Roofs and terraces, parapets, chimneys, sloped gutters and hidden gutters and in many such details.



CUSTOM COLORS SUITABLE FOR ROOFS



Polyethylene Film
 Modified bitumen with SBS or APP
 Glass tissue or polyester reinforcement
 Modified bitumen with SBS or APP
 Aluminium folio

PENGUEN (PLASTOMERIC SERIES) A.P.P. MODIFIED											
TECHNICAL SPECIFICATIONS											
FEATURES	UNIT	SC 2000	SC 3000	SP 3000	SP 4000	SF 40 AR	SP 40 AR	SP 50 AR	SC 3000 AF	SP 3000 AF	SP 4000 AF
REINFORCEMENT		FIBER-GLASS		POLYESTER		FIBER-GLASS	POLYESTER	FIBER-GLASS	POLYESTER		
THICKNESS	MM	2	3	3	4	3,2-3,5	3,2-3,5	4,2-4,5	3	3	4
WIDTH	M	1	1	1	1	1	1	1	1	1	1
LENGTH	M	15	10	10	10	10	10	10	10	10	10
HEAT RESISTANCE	°C	110	110	110	110	110	110	110	110	110	110
COLD FLEXIBILITY	°C	-5	-5	-5	-5	-5	-5	-5	-5	-5	-5
BITUMEN BREAKING POINT (FRAASS)	°C	-15	-15	-15	-15	-15	-15	-15	-15	-15	-15
WATER IMPERMEABILITY	-	✓	✓	✓	✓	✓	✓	✓	✓	✓	✓
LONGITUDINAL (LEAST) TENSE STRENGTH	N/5 CM	300	300	600	600	300	600	600	300	600	600
LTRANSVERSE (LEAST) TENSE STRENGTH	N/5 CM	200	200	400	400	200	400	400	200	400	400
LONGITUDINAL ELONGATION	%	2	2	30	30	2	30	30	2	30	30
TRANSVERSE ELONGATION	%	2	2	30	30	2	30	30	2	30	30
COVERING (FRONT)		PE	PE	PE	PE	MIN	MIN	MIN	AL FOLYO	AL FOLYO	AL FOLYO
COVERING (BACK)		PE	PE	PE	PE	PE	PE	PE	PE	PE	PE

PANDA (PLASTOMERIC SERIES) A.P.P. MODIFIED												
TECHNICAL SPECIFICATIONS												
FEATURES	UNIT	SC 2000	SC 3000	SP 3000	SP 4000	SP 4000 VIA	SF 40 AR	SP 40 AR	SP 50 AR	SC 3000 AF	SP 3000 AF	SP 4000 AF
REINFORCEMENT		FIBER-GLASS		POLYESTER		FIBER-GLASS	POLYESTER	FIBER-GLASS	POLYESTER			
THICKNESS	MM	2	3	3	4	4	3,2-3,5	3,2-3,5	4,2-4,5			
WIDTH	M	1	1	1	1	1	1	1	1	1	1	1
LENGTH	M	15	10	10	10	10	10	10	10	10	10	10
HEAT RESISTANCE	°C	120	120	120	120	120	120	120	120	120	120	120
COLD FLEXIBILITY	°C	-10	-10	-10	-10	-10	-10	-10	-10	-10	-10	-10
BITUMEN BREAKING POINT (FRAASS)	°C	-20	-20	-20	-20	-20	-20	-20	-20	-20	-20	-20
WATER IMPERMEABILITY	-	ü	ü	ü	ü	ü	ü	ü	ü	ü	ü	ü
LONGITUDINAL (LEAST) TENSE STRENGTH	N/5 CM	400	400	800	800	1000	400	800	800	400	800	800
LTRANSVERSE (LEAST) TENSE STRENGTH	N/5 CM	300	300	600	600	800	300	600	600	300	600	600
LONGITUDINAL ELONGATION	%	2	2	35	35	40	2	35	35	2	35	35
TRANSVERSE ELONGATION	%	2	2	35	35	40	2	35	35	2	35	35
COVERING (FRONT)		PE	PE	PE	PE	PE	MIN	MIN	MIN	MIN	MIN	MIN
COVERING (BACK)		PE	PE	PE	PE	PE	PE	PE	PE	PE	PE	PE

FOK (ELASTOMERIC SERIES) S.B.S. MODIFIED								
TECHNICAL SPECIFICATIONS								
FEATURES	UNIT	SC 2000	SC 3000	SP 3000	SP 4000	SF 40 AR	SP 40 AR	SP 50 AR
REINFORCEMENT		FIBERGLASS		POLYESTER		FIBER-GLASS	POLYESTER	
THICKNESS	MM	2	3	3	4	3,2-3,5	3,2-3,5	4,2-4,5
WIDTH	M	1	1	1	1	1	1	1
LENGTH	M	15	10	10	10	10	10	10
HEAT RESISTANCE	°C	100	100	100	100	100	100	100
COLD FLEXIBILITY	°C	-20	-20	-20	-20	-20	-20	-20
BITUMEN BREAKING POINT (FRAASS)	°C	-35	-35	-35	-35	-35	-35	-35
WATER IMPERMEABILITY	-	✓	✓	✓	✓	✓	✓	✓
LONGITUDINAL TENSE STRENGTH (LEAST)	N/5 CM	400	400	800	800	400	800	800
LTRANSVERSE TENSE STRENGTH (LEAST)	N/5 CM	300	300	600	600	300	600	600
LONGITUDINAL ELONGATION	%	2	2	35	35	2	35	35
TRANSVERSE ELONGATION	%	2	2	35	35	2	35	35
COVERING (FRONT)		PE	PE	PE	PE	MIN	MIN	MIN
COVERING (BACK)		PE	PE	PE	PE	PE	PE	PE

PRINCO (PLASTOMERIC SERIES) A.P.P. MODIFIED						
TECHNICAL SPECIFICATIONS						
FEATURES	UNIT	P30	P40	PAR35	PAR40	PAR45
REINFORCEMENT		POLYESTER		POLYESTER	POLYESTER	POLYESTER
WEIGHT	KG/M2	3	4	3,5	4	4,5
WIDTH	M	1	1	1	1	1
LENGTH	M	10	10	10	10	10
HEAT RESISTANCE	°C	110	110	110	110	110
COLD FLEXIBILITY	°C	-10	-10	-10	-10	-10
WATER IMPERMEABILITY	-					
LONGITUDINAL TENSE STRENGTH	N/5 CM	400	400	400	400	400
TRANSVERSE TENSE STRENGTH	N/5 CM	250	250	250	250	250
LONGITUDINAL ELONGATION	%	25	25	25	25	25
TRANSVERSE ELONGATION	%	25	25	25	25	25
COVERING (FRONT)		PE	PE	MIN	MIN	MIN
COVERING (BACK)		PE	PE	PE	PE	PE
ITEM NO.						





SIM SHINGLE

Sim Shingle Unbreakable Shingle



roofing material characteristics of Simshingle make it a good alternative to heavier materials.

FEATURES


- Resistant to bad weather and winds.
- Does not pop out.
- UV resistant.
- Flexible, does not crack or break.
- Not effected by temperature and weather condition changes.
- No peeling of surface minerals.
- Lightweight, very portable and puts no additional load on structures.
- Easily applicable with torch.
- No extra accessories required in fine detail solutions.

Simshingle is an aesthetic roof sheet with detachable film laminated lower surface, natural colored mineral slated upper surface and is composed of fiberglass reinforcement of 110 g/m2 density and high quality APP added bitumen.

Thanks to the sticky nature of bitumen, Simshingle demonstrates perfect adhesion with its adhesive characteristic, highly weatherproof, helpful in fine detailing, maintenance free and quickly applicable.

Easily adaptive to every roof type, Sim Shingle is applied on wooden, metal and/or sloped roofs and on building facades. In addition, it can be applied on curvilinear roofs such as domes and cross vaults. The lightweight

	CLASSIC (Rounded)	HEXAGONAL	EFFECT
Reinforcement	FIBERGLASS		
Width	320mm	320mm	320mm
length	1000mm	1000mm	1000mm
longltudnal Tenslle Strength	600 N/5cm	600 N/5cm	600 N/5cm
Transverse Tenslle Streghth	600 N/5cm	600 N/5cm	600 N/5cm
Net Coverage area (Package)	2.56m2	2.52m2	2.52m2
Packaging Style	POLYETHYLENE COVERED PACKAGES		
Number of leafs (Package)	17 Piece	18 Piece	18 Piece
Package Weight	20kg	17kg	17kg
Softening Point	125 °C	125 °C	125 °C



COLORS



Custom colors available on demand.





SIM SELF (TAPES-MEMBRANES)

SimSelf Tapes (Self-Adhesive)



Areas of usage

Simself tapes are bitumen based waterproofing tapes with one surface covered with aluminium foil or colored minerals and other surface covered with detachable film. Simself tapes are not negatively effected by sunlight due to its natural aluminium folio or natural mineral coating. Thanks to its Flexibility, it can be comfortably applied on curvilinear or skewed surfaces. Simself Tapes, through water tightness and self adhesiveness, present practical solutions in many fine details. It is produced in rolls of 10-15-20-30-60 cm width and 10 meters length.

After the detachable film layer on one side of SimSelf Tape is peeled, the tape is ready to stick. However, to provide a good adhesion, the application surface has to be clean and dry. And on concrete surfaces, Standart bituminous primer should be applied prior to application and after the drying of the primer layer, Sim Self Membrane has to be stucked onto the already dry surface.

Specially made of SBS Modified and self adhesive bitumen. Has 1,5 mm thickness.

COLORS: Natural Aluminium color, Red and Green.

ALUMINIUM FOIL COATED

FEATURES	Unit	Sim Self Tape Aluminium Folio
Thickness	mm	1,5
Weight	Kg/m2	1,7
Width	cm	10-15-20-30-60
Length	m	10
Covering (Front)		AlFolio
Covering (back)		Detachable Film

Specially made of APP Modified and self adhesive bitumen. Contains polyester mat


COLORS: Natural Aluminium color, Red and Green.

MINERAL COATED


FEATURES	Unit	Sim Self Tape with Mineral
Thickness	mm	2,5
Weight	Kg/m2	3
Width	cm	10-15-20-30-60
length	m	10
Carrier		polyester
Covering (Front)		Natural Mineral
Covering (back)		Detachable Film



SIMSELF TAPE (ALUMINIUM FOIL COATED)



SIMSELF TAPE (MINERAL COATED)



"SimSelf tape brings many practical solutions with its waterproofing and self adhesive features"



sim Self Membrane (Self-Adhesive)



details. Its self-adhesive lower surface can easily be applied on heat insulation boards (XPS, EPS, etc.) and materials non resistant to heat such as plastic and wood. In addition, on curvilinear and skewed roofs, its use is very easy and it takes the form of the application surface.

FEATURES


Simself Membrane, which can be produced with mineral coating on one face, can be used as the uppermost layer material on covering. With its self adhesiveness, watertightness and resistance to structural movements, Simself Membranes bring practical solutions to many fine details. Thanks to its flexibility, comfortably applied on curvilinear or skewed surfaces. Produced in rolls of 1 meter width and 10 meters length.

Areas of usage


Since Simself membranes can adhere to various surfaces such as wood, plastic, glass, mortar, concrete and more, they can be used on walls, parapets, chimney flashings, eaves, copings, gable walls, cracks in roof covering tiles, ship deck waterproofing, automotive industry, etc. Especially, where Torch fire is risky or unsuitable to use. Simself can easily be applied on fine

The membrane becomes ready to stick when the film layer is peeled. But to provide a good adhesion, the application surface should be dry and clean. And on concrete surfaces, Standart bituminous primer should be applied prior to application and after the drying of the primer layer, Sim Self Membrane has to be stuck onto the already dry surface.

SimSelf Membrane (Self-Adhesive Bituminous Membrane)						
Features	Unit	SP 1500	SP 2000	SP 2500	"SP 35 AR Mineral Coated "	SP 1500" "Double-sided
Thickness (± 0.2)	mm	1,5	2,0	2,5	3,0	1,5
Weight (± 0.2)	Kg/m ²	2,0	2,5	3,0	3,5	2,0
Width	m	1	1	1	1	1
length	m	10 -15	10 -15	10	10	10
Carrier		polyester	polyester	polyester	polyester	polyester
Coating the surface		Polyethylene film	Polyethylene film	Polyethylene film	Color Mineral	Removable film
Coating substrates		Removable film	Removable film	Removable film	Removable film	Removable film



sim Self Double Sided Membrane (Self-Adhesive)




FEATURES

Application Areas: Since Simself membranes can adhere to various surfaces such as wood, plastic, glass, mortar, concrete and more, they can be used on walls, parapets, chimney ashings, eaves, copings, gable walls, cracks in roof covering tiles, ship deck waterproofing, automotive industry, etc. especially where Torch fire is risky or unsuitable to use. Simself can easily be applied on fine details. Its self-adhesive lower surface can easily be applied on heat insulation boards (XPS, EPS, etc.) and materials non resistant to heat such as plastic and wood. In addition, on curvilinear and skewed roofs, its use is very easy and it takes the form of the application surface.

It is a both sided self adhesive polyester reinforced special polymer bituminous waterproofing membrane. It is used as first layer waterproofing at roofs and construction basements. It brings many practical solutions with its water tightness, compatibility to structures and self adhesiveness.

It can be applied to curved surfaces thanks to its flexibility, it is manufactured in 10 m length rolls with 1,5 mm, 2,0 mm and 3 mm thickness. In cases when torch fire is not preferred to use it can be cold applied. With this feature, it is especially preferred in the renovation of historical buildings. Thanks to its both sided self adhesive feature it achieves a strong adherence between substrate and the second layer membrane.



Method of application: After the film removal the membrane becomes available to adhesion to surface. Membrane is laid to surface directly to adhere the surface. After application, all surfaces especially overlays and joint points must be pressed with silicone rolls so that no bubbles are left and full adhesion is ensured. Before the second layer simself membrane is applied, the upper film of the first applied membrane should be removed and then the below film of the second layer membrane is removed and adhered to the first layer membrane.





INNOVATIVE PRODUCTS



SIMProof Membrane



SIMPROOF MEMBRANE

The SIMPROOF membrane system offers a professional waterproofing solution in deep foundations and single side shear walls. Prevents possible water movements by fully adhesion to structural reinforced concrete. Does not require protective concrete. In the case of possible ground subsidence, the waterproofing is not separated from the reinforced concrete elements.

ADVANTAGES

- It is applied before concrete is poured.
- High performance at below grade and blank mould applications.
- It does not allow lateral water movements by providing complete adhesion with poured structural concrete.
- Its application is fast and easy. Overlaps are self adhesive.
- Waterproofing is also completed along with pouring of concrete.
- It is resistant to water pressure up to 11,5 bar (115 m) after adhesion to concrete.
- The system does not require protective concrete.
- It can be easily cleaned.
- It is not affected by hot / cold phase transitions.
- It is very resistant to subterranean conditions.
- It has salt water resistance.
- It is not effected by ground subsidence.
- It prevents water leaks, hence unnecessary injection costs.


PRODUCT DESCRIPTION

It is a SBS modified and polyester reinforced professional waterproofing membrane with 3.0 - 3.5 - 4.5 mm thickness, covered with a special mineral layer which is loose laid before pouring the concrete and comes into reaction and adheres permanently by hydroheating.




Conventional System

It is the risk that the underground water rises and finds a way through the weak point of the lean concrete, right after finds a way from possible leak of the membrane and travels under the radial base by reaching the protective concrete and raft foundation.



Sim Proof Adhesive System

Sim Proof is a bitumen membrane that sticks to the concrete. Adheres completely to the bottom of the raft concrete and removes the need of protective concrete. It avoid the underground water from reaching the weak insulation of lean concrete and the water movements under the sub base concrete.




SIM Proof Membrane




TOTAL UNIT COST

Traditional Waterproofing Systems



Concrete Bonded Membrane Systems



WATERPROOFING APPLICATION

- Membrane is loose laid.
- The joints are aligned.
- Remove the protective tape
- Joints are adhered and passed over with a printing roller.
- Final checks are made on the membrane.
- Reinforcement can be made before pouring the protective concrete.



sim Marine Membrane



Simmarine membranes are SBS based bituminous elastomeric waterproofing membranes resistant to sea water.

Areas of usage


Harbors, port decks, bridge piers, marina construction and similar areas, structures and buildings on shores.

FEATURES

As known, sea water contains alkali metals, sulfate and some acids. It is necessary to prevent these substances from harming the structure and waterproofing layer protecting the structure. With special additives used in the chemical structure of the marine membrane, higher resistance against alkali metals, sulfate and some acids is achieved. In this type of bituminous membranes, specially formulated elastomeric bitumen is used to enhance resistance to sea water. Polyester mat reinforcement is used to enhance the mechanical resistance to tension. Sim Marine membranes are produced in rolls of 1 meter width and 10 meters length.



Features	Unit	Marine SP3000	Marine SP4000
Reinforcement		Polyester	Polyester
Thickness	mm	3	4
Weight	Kg/m ²	3,5	4,5
Width	m	1	1
Length	m	10	10
Heat resistance	°C	100	100
Cold Bending °C	°C	-20	-20
Longitudinal Tensile str.	N/5cm	800	800
Transverse Tensile Str.	N/5cm	600	600
Covering (Front)		Polyethylene	Polyethylene
Covering (back)		Polyethylene	Polyethylene



Sim Panda VIA



A.P.P Modified bituminous waterproofing membranes to be used in hot, mild and continental (medium cold) climates. Produced at 1 meter width, 10 meters length and at 4 mm thick. Production with both faces polyethylene film covered or one face polyethylene the other thin sand covered are possible. As reinforcement, polyester mat with high durability is used.

Sim Panda Via - Areas of usage

Especially for use in: bridges, viaducts, highways, parking areas, railroads and else areas with similar exposure to very high tension as well as any areas where water leaks into.



Sim Panda Via

Features	Unit	PANDA VIA SP 4000	PANDA VIA SP 4000 thin sand
Reinforcement		Polyester	Polyester
Thickness	mm	4	4
Weight	Kg/ m2	4,8	4,8
Width	m	1	1
Length	m	10	10
Heat resistance	°C	120	140
Cold flexibility	°C	-10	-10
Longitudinal Tensile str.	N/5cm	1000	1000
Transverse Tensile str.	N/5cm	800	800
Covering (Front)		Polyethylene	Thin sand
Covering (Back)		Polyethylene	Polyethylene



Scan QR code for application & intro videos



Polyethylene film
Modified bitumen with APP
High durability Polyester mat
Modified bitumen with APP
Polyethylene film or thin sand




Sim Power VIA



Sim Power Via membranes are double layer polyester mat reinforced, elastomeric (SBS modified) bituminous waterproofing sheets developed especially for structures exposed to extreme tension. Despite being elastomeric, Sim Power Via achieves resistance to very high temperature and with two separate reinforcements in its structure, exhibits an excellent performance against high tension.

Sim Power Via - Areas of usage

Provides waterproofing solution to areas carrying moving loads such as bridges, viaducts, multi storey parking areas, etc. Since in new road projects, Polymeric bituminous mixtures are used in combination with SBS type of additives, SBS Modified bituminous membranes such as Sim Power Via are perfectly suitable for use in both new and old applications.



Sim Power Via

Features	Unit	POWER VIA SP 4000	POWER VIA SP 4000 thin sand
Reinforcement		Polyester	Polyester
Thickness	mm	4	4
Weight	Kg/ m2	4,8	4,8
Width	m	1	1
Length	m	10	10
Heat resistance	°C	140	140
Cold flexibility	°C	-20	-20
Longitudinal Tensile str.	N/5cm	1500	1500
Transverse Tensile str.	N/5cm	1200	1200
Covering (Front)		Polyethylene	Thin sand
Covering (Back)		Polyethylene	Polyethylene



Polyethylene film
Specially modified bitumen with Polyester mat
Specially modified bitumen with SBS
Polyester mat
Specially Modified bitumen with SBS
Polyethylene film

Sim Garden Membrane



Sim Garden Membrane is a waterproofing sheet developed to be used at places such as Gardens and terraces. The basic differences from other bituminous sheets are its special formulation and root resistant film layer (metal-plastic compact carrier) in its structure. Thanks to its specially formulated mixture, Sim Garden does not allow the plant roots to pass through them while the special film layer is a very strong guard against even the strongest roots and keeps them away. Produced in rolls of 1 meter width and 10 meter length at 3 mm or 4 mm thicknesses. Elastomeric Sim Garden is made of Styrene Butadine Styrene (SBS) Modified bitumen and plastomeric Sim Garden is made of Atactic Polypropylene (APP) Modified bitumen.

Areas of usage



Generally used to achieve watertightness on terrace roofs of structures. In external basement tanking, foundation and curtain wall applications.

On all surfaces in somehow contact with soil and on all surfaces, requiring flexibility, in contact with soil and water.

Garden, Garden terrace, Garden balcony, parking area, etc. Also, for waterproofing in external basement tanking, foundation and curtain walls...



Features	Unit	PLASTOMERIC		ELASTOMERIC	
		SP 3000	SP 4000	SP 3000	SP 4000
Reinforcement		Polyester			
Thickness	mm	3	4	3	4
Width	m	1	1	1	1
Length	m	10	10	10	10
Heat resistance	°C	120	120	100	100
Cold Bending	°C	-10	-10	-20	-20
Longitudinal Tensile strength	N/5cm	800	800	800	800
Transverse Tensile Strength	N/5cm	600	600	600	600
Covering (Front)		Polyethylene	Polyethylene	Polyethylene	Polyethylene
Covering (back)		Polyethylene	Polyethylene	Polyethylene	Polyethylene



sim Garden Membrane



sim SELF CROSS LAMINATED MEMBRANE

NEW PRODUCT



- Flat decks
- Plaza decks / Roof gardens / Terraces
- In wet spaces, on retaining walls
- In the protection and insulation of building and building elements exposed to temporary or permanent water pressure to leakage water
- External insulation of water tanks
- For the insulation of underground garages and car parking lots

Advantages

- Easy to prepare and easy to apply
- No Torch, no hot air supply required
- It adheres fully to the applied surface
- Combined flexible membrane and waterstop system for security
- Applicable on vertical and horizontal surfaces
- Provides insulation after application without requiring drying time
- Crack bridging feature
- Provides dimensional stability and puncture resistance

Technical Specifications

- > Upper Surface: Cross Laminated High Density Polyethylene Film HDPE
- > Lower Surface: Silicone Film
- > Color: Black
- > Installation Temperature: +5 oC 35 oC
- > Thickness: 1,5 mm
- > Weight: 2 kg/m2

Packaging

20 m2 rolls in carton boxes.


Product Description


It is a high performance, cold applied, flexible, preformed waterproof membrane combining a special high performance cross-laminated, HDPE carrier film with a unique self-adhesive bitumen compound. Specifically designed for applications on foundations and to be used as a sealing element in vertical and horizontal waterproofing applications. Silicone film on the bottom surface is removed to provide easy and permanent insulation

Application Areas

- Basement and Curtain Walls
- Sub-structures

Cross Laminated HDPE Film
Self Adhesive Layer
Release Film






PVC PANELS



PI PLAK



ADVANTAGES OF USE

- Gives exposed concrete. No need for mortaring. Helps applications of direct plastering or painting.
- Custom length available on demand.
- Resistant to drilling and cutting.
- Saves you the cost of epoxy coating needed to make plywood watertight.
- Long lasting unlike plywood.
- UV resistant.


CONCRETE FORM USAGE

PI PLAK is an ideal product especially in concrete forms to get exposed concrete where more times of usage is demanded.


Environment friendliness and high resistance to corrosion due to its durability against chemical reactions make it a suitable and profitable choice in formwork. In comparison to plywood, it has lower durability but using shorter purlin spacing, PI PLAK gives smoother concrete in the end with no need for mortaring.

PANEL SIZES

- Standard dimensions 2500x1250 mm
- Special dimensions upon demand
- Thickness 3 mm- 24 mm + / - %2
- Length/width tolerance is + / - 1 mm per meter
- Diagonal Rectangular Tolerance + / - 1 mm per meter



SimForeks



Sim Power Forex can be used in Steel Molds. Forex can be used in steel molds due to its flexible and solid structure and 1000kg/m³ density. Sim Power Forex's solid body and fractural resistance increases the number of use in steel molds, allows more use compared to plywoods.



General Product Information / Description of the product Sim Forex:


Compact Laminate Sheet (Sim Power Forex) with its flexible and solid structure of 1000kg / m³ density, can be used in steel molds, wet floors, containers and in many areas. Sim Power Forex with its solid body and fractural resistance is easy to use and can be used in any weather condition.




- Dimensions
250cm X 130 cm
1000 Kg/m³ Density



Scan QR code for application & intro videos





LIQUID PRODUCTS

SIM Astar (Primer)



Standart ASTAR; a ready to use waterproofing material obtained by mixing water and bitumen through special methods.

Standart Astar is used before the Standart bituminous membrane application. With advanced adhesion feature gives the Standart bituminous membrane a more durable and spaceless adhesion.

Consumption: 400 g/m² every use
Bucket: Net 17 kg / Plastic Bucket



SimEx 2K



Features

- Easily applied (brush, roll or trowel)
- Adheres perfectly to mineral surfaces such as concrete, stone, brick, briquet.
- Flexible, crack covering capacity is high.
- Must be applied cold. Does not require heating or diluting.
- Water based. Environment friendly.

Application

- Because it does not contain ammable or toxic substances, usage in closed areas is safe.
- Applies seamlessly since there is no overlap or joint. Cures fast.
- Surface preparation must be done prior to installation. For this reason, necessary repairing must be done and the surface should be freed from dust, stain, oil and loose layers that will hamper adhesion.
- Chamfering must be done at corner turns.
- Should not be applied in rainy weather or at temperatures below +5 C.
- Angle the vertical and horizontal corners by chamfering.
- Apply with 70-90 g/m2 density special insulation net to bridge the vertical and horizontal joints and cracks and to solidify wide surfaces.
- To achieve good adhesion, apply standart primer on the surface.
- Dries in 1-2 hours depending on the weather conditions.
- Should be applied in two layers at least. Before one layer dries, the other layer should not be applied.

Enhanced bitumen based, double component, water based elastic waterproofing materials.

Areas of usage

- On vertical and horizontal surfaces, foundations and foundation curtain walls.
- Surfaces constantly under soil and in contact with water. external proofing of places such as cellars and basements.
- Wet areas such as bathrooms, kitchens and toilets.
- balconies and terraces (covering up).



Scan QR code for application & intro videos



Packing Style

A+b component in 30 kg Plastic Bucket
Liquid : 22 kg - Powder : 8 kg

Storage

5-30 C, vertically, in covered areas.

Consumption

Used at 1,1 kg/m2 density The thickness depends on the structure of application surface and water pressure on the surface

SimPolas



Features

- Due to the special additives in its composition, highly durable, blanketing and flexible in comparison to traditional primers.
- Easily applied (Brush or roll)
- Must be applied cold. No heating or diluting required.
- Water based, environment friendly.
- Because it does not contain ammable or toxic substances, usage in closed areas is safe.
- Applies seamlessly since there is no overlap or joint.

Bitumen based, rubber Modified, single component water based, flexible, liquid waterproofing materials. Its color is brown prior to application. After drying its color turns blackish.

Areas of usage

- In wet areas such as bathrooms, kitchens and toilets.
- On vertical surfaces such as balconies and small terraces.
- Used as protection against moisture and on vertical surfaces such as curtain walls in foundations
- On multi storey insulations, roofs, balconies and wet areas with armatures like fiberglass, bituminous cardboard, canvas to achieve watertightness.

Packaging Style

in 17 kg plastic bucket.

Storage

5-30 C. in vertical position in closed areas.

Application:

- Because it fully adheres to surfaces, its watertightness is perfect.
- Can be applied on humid surfaces.
- A thicker bitumen layer can be obtained by adding fiberglass between layers.
- Surface preparation must be done prior to installation. For this reason, necessary repairing must be done and the surface should be freed from dust, stain, oil and loose layers that will hamper adhesion.
- Angle the vertical and horizontal corners by chamfering.
- To achieve a good adhesion to the surface, especially on not completely clean surfaces, water based Standart Bitumen Emulsion must be applied as a primer and be waited for to dry away prior to application.
- After opening and mixing thoroughly, apply the product on the surface using a roll or brush.
- Should not be applied in rainy weather or at temperatures below +5 C.
- Should be applied in two layers at least. Before one layer dries, the other layer should not be applied.
- A protective panel should be placed following the application on foundation curtain walls
- No pedestrian traffic or no kind of load should be allowed until drying is complete.
- Should be reinforced with fiberglass depending on the size of the application area.



simplan
SYNTHETIC
WATERPROOFING
SHEETS

PVC
Homogenous, UV resistant,
Reinforced, PVC Waterproofing
Membranes

SYNTHETIC MEMBRANES

SIMPLAN BASECAP

Homogenous PVC Waterproofing Membrane UV incompetent, vapor permeable, without reinforcement SOFT PVC waterproofing Membrane. it can be adhered with hot air welder.

APPLICATION AREAS:

- Building foundation and wall waterproofing
- Waterproofing of underground galleries
- Ballasted Roofs
- Wet areas
- Highway, subway tunnels
- Hangar and planking
- Concrete Roofs
- Building Dilatation Systems



APPLICATION ADVANTAGES:

- High Quality meeting EN 13967 Quality Standards
- Vapor Permeable structure
- Plant Root Resistance
- Recyclable environment-friendly material that includes no heavy metal
- Homogenous product against corrosion and dissolution
- Highflexibility value. Material which has dimensional stability
- Ability to maintain its flexibility in -25C degrees temperature
- High tear resistance and impact strength
- Qualified and easy application options with heat air welder.
- Provides waterproofing in temperatures between -35 C and +85 C degrees



Features	Minimum Required Value	Test Result	Unit	Test Method
Determination of watertightness	Impermeable	Impermeable	-	EN 1928 (B)
Determination of watertightness post aging test	Impermeable	Impermeable	-	EN 1296 ve EN 1928 (A)
Determination of visible defects	No defect	No defect	-	EN 1850-2
Tensile strength	> 15	> 18	N/mm2	EN 12311-2
Flexibility/ Elongation at break	> 250	> 300	%	EN 12311-2
Resistance to static loading	> 20	> 22	Kg	EN 12730 (B)
Resistance to impact	> 450	> 800	mm	EN 12691 (A)
Resistance to tearing (nail shank)	> 300	> 330	N	EN 12310-1
Reaction to Fire	E Class	E Class	-	EN 13501-1
Shear resistance of joints	> 600	> 800	N/50mm	EN 12317-2
Water vapour transmission properties	25500±7500	25500±7500	μ	EN 1931
Determination of peel resistance of joints	> 150	> 155	N/50 mm	EN 12316-2
Dimensional Stability	< 2	< 2	%	EN 1107-2
Determination of foldability at low temperature	< -25	< -25	°C	EN 495-5

Product Sizes :

Thickness	Width	Length	Colour*	Roll m ²	Roll Weight
1,2 mm	2 mt	25	Black	50 m ²	81 kg
1,5 mm	2 mt	20	Black	40 m ²	81 kg
1,8 mm	2 mt	20	Black	40 m ²	97 kg
2,0 mm	2 mt	15	Black	30 m ²	84 kg

(*) Different colors available on demand



SIMPLAN BASECAP SIGNAL

Homogenous PVC Waterproofing Membrane UV incompetent, vapor permeable, without reinforcement, SOFT PVC waterproofing with signal layer. it can be adhered with hot air welder.

APPLICATION AREAS:

- Building foundation and wall waterproofing
- Ballasted Roofs
- Wet areas
- Waterproofing of underground galleries
- Highway and subway tunnels
- Hangar and planking
- Concrete Roofs
- Dilation of Building Systems



APPLICATION ADVANTAGES:

- High Quality meeting EN 13967 Quality Standards
- Vapor Permeable structure
- Plant Root Resistance
- Recyclable environment-friendly material that includes no heavy metal
- Homogenous product against corrosion and dissolution
- High flexibility value. Material which has dimensional stability Ability to maintain its flexibility in -25C degrees temperature
- High tear resistance and impact strength
- Qualified and easy application options with heat air welder.
- Provides waterproofing in temperatures between -35 C and +85 C degrees



Features	Minimum Required Value (EN)	Test Result	Unit	Test Method
Determination of watertightness	Impermeable	Impermeable	-	EN 1928 (B)
Determination of watertightness post aging test	Impermeable	Impermeable	-	EN 1296 ve EN 1928 (A)
Determination of visible defects	No defect	No defect	-	EN 1850-2
Tensile strength	> 15	> 18	N/mm ²	EN 12311-2
Flexibility/ Elongation at break	> 250	> 300	%	EN 12311-2
Resistance to static loading	> 20	> 22	Kg	EN 12730 (B)
Resistance to impact	> 450	> 800	mm	EN 12691 (A)
Resistance to tearing (nail shank)	> 300	> 330	N	EN 12310-1
Reaction to Fire	E Class	E Class	-	EN 13501-1
Shear resistance of joints	> 600	> 800	N/50mm	EN 12317-2
Water vapour transmission properties	25500±7500	25500±7500	μ	EN 1931
Determination of peel resistance of joints	> 150	> 155	N/50 mm	EN 12316-2
Dimensional Stability	< 2	< 2	%	EN 1107-2
Determination of foldability at low temperature	< - 25	< - 25	°C	EN 495-5

Product Sizes :

Thickness	Width	Length	Colour*	Roll m ²	Roll Weight
1,2 mm	2 mt	25	Yellow-Black	50 m ²	81 kg
1,5 mm	2 mt	20	Yellow-Black	40 m ²	81 kg
1,8 mm	2 mt	20	Yellow-Black	40 m ²	97 kg
2,0 mm	2 mt	15	Yellow-Black	30 m ²	84 kg

(*) Different colors available on demand



SIMPLAN WATERCAP

Homogenous PVC Waterproofing


Membrane for Drinking Water Reservoirs Vapor permeable, without reinforcement, Anti – Bacterial, applied to drinking and potable water tanks SOFT PVC waterproofing membrane. it can be adhered with hot air welder easily.

APPLICATION AREAS:

- Drinking Water Reservoirs and Tanks as Top Layer
- Water Channels and Water Tanks as Top Layer
- Drinking and Potable water transmission systems

APPLICATION ADVANTAGES:

- High Quality meeting EN 13967 Quality Standards
- Vapor Permeable structure
- Antimicrobial Features
- Does not change of water physical and chemical properties
- Does not permit generation of bacteria and mosses on the surface.
- Recyclable environment friendly material that includes no heavy metal
- High flexibility value. Dimensionally stable material
- Ability to maintain its flexibility in -25C degrees temperature
- High tear resistance and impact strength
- Qualified and easy application options with heat air welder
- Provides waterproofing in temperatures between -35 C and +85 C degrees
- Homogeneous product that has dissolution and decomposition resistances




Features	Minimum Required Value (EN)	Test Result	Unit	Test Method
Determination of watertightness	Impermeable	Impermeable	-	EN 1928 (B)
Determination of watertightness post aging test	Impermeable	Impermeable	-	EN 1296 ve EN 1928 (A)
Determination of visible defects	No defect	No defect	-	EN 1850-2
Tensile strength	> 15	> 18	N/mm ²	EN 12311-2
Flexibility/ Elongation at break	> 250	> 320	%	EN 12311-2
Resistance to static loading	> 20	> 20	Kg	EN 12730 (B)
Resistance to impact	> 450	> 900	mm	EN 12691 (A)
Resistance to tearing (nail shank)	> 300	> 330	N	EN 12310-1
Reaction to Fire	E Class	E Class	-	EN 13501-1
Shear resistance of joints	> 600	> 750	N/50mm	EN 12317-2
Water vapour transmission properties	25500±7500	25500±7500	μ	EN 1931
Determination of peel resistance of joints	> 150	> 155	N/50 mm	EN 12316-2
Dimensional Stability	< 2	< 2	%	EN 1107-2
Determination of foldability at low temperature	< - 25	< - 25	°C	EN 495-5

Product Sizes :

Thickness	Width	Length	Colour*	Roll m ²	Roll Weight
1,2 mm	2 mt	25	Blue	50 m ²	81 kg
1,5 mm	2 mt	20	Blue	40 m ²	81 kg
1,8 mm	2 mt	20	Blue	40 m ²	97 kg
2 mm	2 mt	15	Blue	30 m ²	84 kg

(*) Different colors available on demand



SIMPLAN LAKECAP - UV

Homogenous PVC Lake Membrane UV resistant, vapor permeable, without reinforcement PVC Waterproofing Membranes have plant root resistance, they can be used for artificial lakes and dam applications and can be adhered with hot air welder.

APPLICATION AREAS:

- Construction of artificial lakes as Top layer.
- Construction of Garden pools and fish lakes.
- Construction of Decorative pools and lakes.

APPLICATION ADVANTAGES:

- High Quality meeting EN 13967 Quality Standards
- Vapor Permeable structure
- Plant Root Resistance
- UV Resistant
- Durable against atmosphere conditions
- Recyclable environment-friendly material that includes no heavy metals
- Homog- enous product that has dissolution and decomposition resistances
- High flexibility value. Material which has dimensional stability
- Ability to maintain its flexibility in -25C degrees temperature
- High tear resistance and impact strength
- Qualified and easy application options with heat air compressor
- Provides waterproofing in temperatures between -35 C and +85 C degrees



Features	Minimum Required Value (EN)	Test Result	Unit	Test Method
Determination of watertightness	Impermeable	Impermeable	-	EN 1928 (B)
Determination of watertightness post aging test	Impermeable	Impermeable	-	EN 1296 ve EN 1928 (A)
Determination of visible defects	No defect	No defect	-	EN 1850-2
Tensile strength	> 15	> 18	N/mm2	EN 12311-2
Flexibility/ Elongation at break	> 250	> 320	%	EN 12311-2
Resistance to static loading	> 20	> 20	Kg	EN 12730 (B)
Resistance to impact	> 450	> 900	mm	EN 12691 (A)
Resistance to tearing (nail shank)	> 300	> 330	N	EN 12310-1
Reaction to Fire	E Class	E Class	-	EN 13501-1
Shear resistance of joints	> 600	> 750	N/50mm	EN 12317-2
Water vapour transmission properties	25500±7500	25500±7500	μ	EN 1931
Determination of peel resistance of joints	> 150	> 155	N/50 mm	EN 12316-2
Dimensional Stability	< 2	< 2	%	EN 1107-2
Determination of foldability at low temperature	< - 25	< - 25	°C	EN 495-5

Product Sizes :

Thickness	Width	Length	Colour*	Roll m ²	Roll Weight
1,5 mm	2 mt	20	Yellow	40 m ²	81 kg
1,8 mm	2 mt	20	Yellow	40 m ²	97 kg
2,0 mm	2 mt	15	Yellow	30 m ²	84 kg

(*) Different colors available on demand



SIMPLAN LAKECAP - UV PLUS


UV Resistant, Polyester Reinforced PVC Lake Membrane UV resistant, polyester reinforced and vapor permeable REINFORCED PVC Waterproofing Membranes have plant root resistance, they can be used for artificial lakes and dam applications and can be adhered with hot air welder.

APPLICATION AREAS:

- Used in dam applications
- Used in irrigation channels in agricultural lands
- Used as final layer while constituting artificial lakes
- Used for constituting Garden and fish artificial lakes.
- Used for constituting ornamental pools and decorative lakes.

APPLICATION ADVANTAGES:

- High Quality meeting EN 13956 Quality Standards
- Vapor Permeable structure
- Plant Root Resistance
- UV Resistant / Durable against atmosphere conditions
- Recyclable environment-friendly material that includes no heavy metal
- Polyester reinforced product that has dissolution and decomposition resistances.
- High flexibility value. Material which has dimensional stability
- Free layout usage feature by means of mechanically xing method
- Ability to maintain its flexibility in -25C degrees temperature
- High tear resistance and impact strength
- Qualified and easy application options with heat air welder
- Provides waterproofing in temperatures between -35 C and +85 C degrees



Features	Test Result	Unit
Determination of visible defects	No defect	-
Determination of watertightness	> 420	KPa
Resistance to root penetration	Feasible	-
UV resistance (1000 h)	Resistant	-
Shear resistance of joints	> 850	N/50 mm
Resistance to static loading	> 25	Kg
Flexibility/ Elongation at break	> 35	%
Resistance to impact	850	mm
Water vapour transmission properties	25000±7500	μ
Resistance to tearing (nail shank)	> 220	N
Tensile strength	>1100	N/50 mm
Determination of peel resistance of joints	> 300	N/50 mm
Determination of foldability at low temperature	<- 25	°C
Dimensional Stability	< 1	%
Hail resistance	> 19	m/s

Product Sizes :

Thick-ness	Width	Length	Colour*	Roll m ²	Roll Weight
1,5 mm	2.10 mt	20	Yellow	42 m ²	87 kg
1,8 mm	2.10 mt	20	Yellow	42 m ²	104.5 kg
2,0 mm	2.10 mt	15	Yellow	31.5 m ²	89 kg

(*) Different colors available on demand



SIMPLAN ROOFCAP - UV

UV Resistant, Polyester Reinforced PVC Roof Membrane UV resistant, polyester reinforced and vapor permeable REINFORCED PVC Waterproofing Membranes have plant root resistance, they can be used for roof waterproofing applications and can be adhered with heat air welder.

APPLICATION AREAS:

- Steel roofs and ligh metal roofs
- Garden terrace roofs
- Parking lot terrace roofs
- Concrete roofs and parapets

APPLICATION ADVANTAGES:

- High Quality meeting EN 13956 Quality Standards
- Vapor Permeable structure
- Plant Root Resistance
- UV Resistant / Durable against atmosphere conditions
- Recyclable environment-friendly material that includes no heavy metal
- Polyester reinforced product that has dissolution and decomposition resistances.
- High flexibility value. Material which has dimensional stability
- Free layout usage feature by means of mechanically xing method
- Ability to maintain its flexibility in -25C degrees temperature
- High tear resistance and impact strength
- Qualified and easy application options with heat air welder
- Provides waterproofing in temperatures between -35 C and +85 C degrees




Features	Minimum Required Value (EN)	Test Result	Unit	Test Method
Determination of visible defects	No defect	No defect	-	EN 1850-2
External fire exposure	B Roof (t1)	Feasible	-	EN 13501-5
Reaction to Fire	E Class	E Class	-	EN 13501-1
Determination of watertightness	> 400	> 420	KPa	EN 1928 (B)
Resistance to root penetration	Feasible	Feasible	-	EN 13948
UV resistance (1000 h)	Resistant	Resistant	-	EN 1297
Shear resistance of joints	> 800	> 800	N/50 mm	EN 12317-2
Resistance to static loading	> 20	> 25	Kg	EN 12730 (B)
Flexibility/ Elongation at break	> 15	> 35	%	EN 12311-2
Resistance to impact	> 400	900	mm	EN 12691 (A)
Water vapour transmission properties	25000±7500	25000±7500	μ	EN 1931
Resistance to tearing (nail shank)	> 180	> 220	N	EN 12310-2
Tensile strength	> 800	>1000	N/50 mm	EN 12311-2
Determination of peel resistance of joints	> 200	> 300	N/50 mm	EN 12316-2
Determination of foldability at low temperature	< - 25	< - 25	°C	EN 495-5
Dimensional Stability	< 1	< 1	%	EN 1107-2
Hail resistance	> 17	> 19	m/s	EN13583

Product Sizes :

Thickness	Width	Length	Colour*	Roll m ²	Roll Weight
1,2 mm	2,10 mt	25	Gray / Black	52,5 m ²	87 kg
1,5 mm	2,10 mt	20	Gray / Black	42 m ²	87 kg
1,8 mm	2,10 mt	20	Gray / Black	42 m ²	104,5 kg
2,0 mm	2,10 mt	15	Gray / Black	31,5 m ²	89 kg

(*) Different colors available on demand





COMPLEMENTARY PRODUCTS

SIM DRAINAGE BOARD



and on surfaces with no static load, the drainage boards are used as a substitute for lean concrete as they are very useful, functional, cost saving as well as being environment friendly.


Areas of usage

- Floors, basements and curtain walls
- Terrace Roof applications
- Parking Areas
- Tunnels
- Generally in all structures that must be protected from water and its consequential pressure




Made of high density polyethylene Stadren Drainage boards, with their dimpled structure, separates the building from soil thereby providing water drainage. Protects the heat and water proofing materials on curtain walls from plant roots, various chemicals and the mechanical effects of earth fill. In terrace Garden applications

FEATURES

- Through convenient application, Stadren drainage boards help keep your building safe from water, soil and the harmful effects of various chemicals.



FEATURES	400 GR/M ²	500 GR/M ²	600 GR/M ²
RAW MATERIAL	HDPE		
THICKNESS	0,4 mm	0,5 mm	0,6 mm
DIMPLE HEIGHT	8,0 mm	8,0 mm	8,0 mm
WEIGHT	450-500 g/m ²	550-600 g/m ²	650-700 g/m ²
PRESSURE RESISTANCE	170 kN/m ²	230 kN/m ²	320 kN/m ²
UNDER SOIL RESISTANCE	Against plant roots, impacts and all chemicals.		
HEAT RESISTANCE	BETWEEN 30 C AND 80 C		
COLOR	Black		
ROLL LENGTH	20 mt		
ROLL WIDTH	2 mt		



Polyethylene film
 Modified bitumen with APP
 Glass tissue or polyester reinforcement
 Modified bitumen with APP
 Polyethylene Film



SIMFIX Polyurethane Sealant

Sim Fix is a single component, moisture curing, polyurethane based sealant material.

Usage and application area

Is capable of adhesion to cementbased building materials, brick, ceramic, marble, glass, wood, galvanize steel, aluminum and most plastic surfaces. Used in construction industry, in the cavities of the joints between building elements. Used for joints and assembly of aluminum, PVC, wooden framing. Used for laying of roof tiles.

FEATURES

- One-component.
- Easy application with gun.
- Thixotropic.
- Cures with the humidity in the air.
- Paintable
- No volume change.
- Resistant to weather conditions and water.
- Permanent elasticity.



300ml



600ml



SIM Plan PVC Complementary Products



Parapet Strainer Outlets 1- Round outlet parapets (Ø50 – Ø70 -Ø100)

As with all of our other products, parapet nished lters Show a precise and perfect combination with our insulation solutions and materials resulting in perfect waterproofing.




Strainers with vertical outlets Product Description (Ø50 – Ø70 -Ø100 -Ø125 -Ø150)

Balcony and terrace lters with vertical downslopes are manufactured specially from single piece PVC. This piece, removes the possibility of water leaks at risky points.



Leaf holders

On sloped roofs into the PVC drain holes and on terrace roofs without ceramic or tiles or ventilation shafts, leaf holders are used to prevent large objects from blocking the pipes. Resistant to UV rays, climate conditions and chemical substances. Application: The lower part of the leaf holder is pressed into the mouth of the drainage pipe to achieve a tight positioning. Sizes: is available for use at all diameters between 50 and 160 mm.



Screws

We have 5 different screws: 1-Concrete screws 2-Trapeze screws 3-Panel screws 4-insulation screws 5-Wood Screws

Flashing:

These aluminium materials are used in watertanks, parapets, curtain insulation, at the begin- ning and nishing of drainage boards and geomembranes; help xing downwards like a curta- in; and as well, help keeping wa- ter away from seeping between the membrane and the Wall.



TWIN DRAINAGE SYSTEMS AND ACCESSORIES

Usage: On terraces, roofs and balconies, water, once inside, travels along the insulation layer down to the drainage pipe. The pooling water can not evaporate and continues its journey into deeper layers ,consequently leading to dark spots due to moisture. The twin drainage system is used to prevent these dark spots. The medium piece that connects to the lower drainage piece is made of polypropylene, seats perfectly into lower drainage piece and thanks to the 0,6 mm gaps, makes up another drainage helping the leaking water ow into the drainage pipes.



inner and Outer Corner Apparatus

in terms of waterproofing water tanks, terrace roofs are risky places when it comes to covering corners. These materials can be used at such places.



Flanged Strainer Waterproofing Systems

System Parts
a) Body – Lower outlet – Side Outlet
b) Flange ring
c) Upper strainer body
d) Upper strainer grid
e) Odor Filter Piece

Usage:

The chosen strainer body is seated into the laying and mounted on the pipe. The ange ring is placed, the height of the strainer lter is adjusted and then the ange ring is fastened. The holes aside the upper strainer body are to drain the remaining water directly into the drainage pipe. The channels on the outer surface of the body can be cut during height adjustment and when needed they can be slot into each other. The grids we produce at 10*10 cm and 15*15 cm give you more choices.

Roof Connection Elements. Fixings

We have two types of Fixings.
1- Clawed Concave Fixings
2- Round Fixings



Ventilation Shafts

Ventilation Shafts help keeping the insulation layer dry by transferring out the moisture and vapor inside the structure and should be used at every 25-50 meters.


Sim Bituminous Membranes Complementary Products



Twin Loss System and Accessories

It proceeds on the insulation layer until the points where discharge pipes are located after reaching the water insulation layer on terrace roofs and balconies. The water accumulating on this point proceeds towards lower layers as it does not evaporate and it causes the formation of damp-related black stains.

Twin loss system is used to prevent such stains. The connecting piece enabling connection to the lower loss part is made up of propylene. It fits to the lower loss part perfectly and makes the leaking water flow into discharge pipes by constituting a second loss line thanks to the 0.6mm gaps.



Parapet Filters

We have two parapet output filter models.

1- Vertical Outlet Parapet (10 X 10cm square)

2- Round Outlet Parapet (Ø50 – Ø70 -Ø100) Trouble free impermeability can be achieved by maintaining a perfect harmony through the insulation materials and methods used as in our other products.




Filters Vertical Outlets

Product Introduction :

(Ø50 – Ø70 -Ø100 -Ø125 -Ø150) Vertical outlet and terrace outlet materials are produced as single parts from a special material called dutrel. This part removes the water leakage risk on potential points. They get into other water insulation materials especially bitumen water insulation covers.

Their lower surfaces are elastic and heat resistant. Thus, it enables a wonderful connection which you can combine with bitumen water insulation covers as well as other insulation covers in a perfect way. This connection has no leakage risks and it is never affected by thermal changes




Sliding Insulation Systems

Compatible Expense System Parts

a) Loss Body With Bottom Output (2001, 2002, 2048) With Side Output (2000, 2004, 2005)

b) Upper filter grid (1010, 1011, 2010)

c) Anti-odor connection part (1015) Anti-odor connection part can be used only for side outputs.



Shingle Ventilation Shaft

Membrane Ventilation Shaft h=32cm Inclined Roof (Shingle) Ventilation Shaft: Shingle ventilation shafts are used if the roof insulation covers located on inclined roofs are shingle or slated. Usage number varies according to the roof bent. Straight Model (Black -Red - Green) Capped Model (Black - Red - Green)



Sim Shingle nails

It is sold in 2.5kg boxes (sizes 1,5cm-2cm-2,50cm-3,00cm)



Geotextile Fleece

Due to its high puncture resistance fleece protects materials from impacts, enables various working styles and prevents cement grout from leaking down.

Because it helps spread the pressure, it is used for waterproofing in building foundations.

Protects the geomembranes applied on exposed surfaces against tearing and overfriction.

Especially: in building foundations, foundation walls, curtains, terraces, roofs, metro tunnels and roadway tunnels.




Leaf Holders

It is used on inclined roofs for preventing leaves and similar objects from falling into PVC roof valleys. It is also used on terrace roofs and ventilation shafts on which ceramics or tiles have been paved for preventing leaves and similar objects (objects big enough to block the pipes) from falling into pipes. It is not affected by ultraviolet rays, climate conditions and chemical substances.


Application: Leaf holder is made to stay inside the discharge pipe by compressing and inserting it into the discharge pipe.

Measure: It is appropriate to be used for all diameters from 50 to 160 mm.



Apparatus Inner and Outer Corner

These are the auxiliary materials facilitating the application on corner turns which constitute the risky areas in terrace water insulation application.



Standart insulation Pins

Used to fasten insulation materials on vertically sloped surfaces. Self adhesive Standart pins can only be used on smooth, plain, clean and dry surfaces. The sticky surface should not be touched. Metal surface or ambient temperature should be no more than 5 C. The expected adhesion comes 12 hours later. The amount to be used depends on density or weight of the material, temperature and the surface conditions. In many applications, depending on the surface and construction site conditions, 5 -9 pieces/ m2 are generally sufficient.

A-METAL POLYETHYLENE INSULATION PIN

STANDARD PIN	Package Quantity
40 MM (4 CM)	500 Pcs
60 MM (6 CM)	500 Pcs

B-PLASTIC BITUMEN INSULATION PIN

STANDARD PIN	Package Quantity
40 MM (4 CM)	500 Pcs
60 MM (6 CM)	500 Pcs



Horizontal Outlet Strainers

Designed to complete the drainage pipes used in all horizontal outlet terrace and roof strainers and shares all the features with the vertical outlet version. It comes in 50 70 and 100 mm diameters.



Flanged Waterproofing Systems Expense System Parts

- a) Loss Body-Bottom Output-Side Output
- b) Flange Ring
- c) Upper filter body
- d) Upper filter grid
- e) Anti-odor connection part

Use : Chosen loss body is placed on the flooring and adapted into the PVC pipe. If sliding materials are to be used as insulation materials, the loss line will be integrated into concrete flooring thanks to the file you put under the body. Flange ring is fixed after it is located in its place and the height of the upper filter body to be placed on top is adjusted.

The gaps near upper filter body enable leaking water to go directly in to the discharge pipe. The channels on the outer surface of body have been designed in such a way that they can be cut off while adjusting the height and when necessary their height can be increased by inserting them into each other. Plastic and stainless grids we produce in 10*10cm and 15*15cm sizes give you a chance to make your choice.



Ventilation Shafts

Ventilation Shafts help keeping the insulation layer dry by transferring out the moisture and vapor inside the structure and should be used at every 25-50 meters in bituminous membra- fine applications.

simBoard XPS (Extrude Polystyrene Sheets)



FEATURES

- Thermal insulation coefficient is compliant with the offered values.
- Mechanical durability is ideal. (22-32 kg/m³)
- With its high vapor di usion resistance it does not require extra vapor barrier. MÜ= M
- E-B1 fire classs
- Produced to fit the density requirements of where it will be used (roof, Wall, flooring).
- Edges are tongued and grooved.
- Compliance with the building physics is stable.
- The insulating abilities of 3 cm WALLBOARD equal to: 5 cm glass wool, 31 cm autoclaved concrete block, 63 cm aerated brick and 264 cm concrete.

Used in exterior and interior insulation, roof thermal insulation, XPS is made from polystyrene which is obtained through the polymerization of petroleum byproduct styren monomer.

Some instances of installation are:

- Plain terraces and sloped roofs
- Under the balconies
- Unwarmed areas like garages and warehouses
- Plumbing pipes
- Ventilation channels

Considering the need for the energy in the cooling of the buildings is around 4 times as much as the energy needed for heating, the total energy consumption of Turkey can be reduced by 15-20%.

Panel Dimensions

Dimension: Width 60 X Length 125-300 mm

Thickness: 2-3-4-5-6-7-8cm
Length/width tolerance (per meter) Squareness tolerance (diagonal per meter)



ROCK WOOL Thermal, Sound and Fire Insulation



It is used for the purpose of heat, sound and water insulation in the roof terrace. It is an uncoated mineral plate. It is produced by melting and fibering of basalt totally native raw material under high temperatures. It can also be manufactured in the form of mattresses, bulk, sheet and pipe by using a coating material. Insulawool is the insulation material within the mineral wools and has high sound insulation properties besides its thermal insulation. Insulawool products can be used between -50 / +750C range. It is an A class inflammable material pursuant to TS EN 13501. It has dimensional stability and it does not change its measures under the effect of temperature and humidity. Mattress and sheet type products are produced in compatibility with TS 901-1 EN 13162 standard.

Areas of usage

Water Repellent Feature:

During production water repellency has been brought with silicone addition to terrace plates.

APPLICATION AREAS:

- Concrete or trapezoidal metal, flat or any kind of sloping roofs.
- Walking or not walking flat roofs

Usage Areas:

- Thermal insulation
- Sound insulation
- Fire protection

FEATURES

- **Surface Coatings:** It can be also produced with the following surfaces.
 - Aluminum folio
 - Fiberglass
- **One side aluminum folio, other side with fiberglass or both side fiberglass**
- **Fire resistance:** It is an A class inflammable material pursuant to TS EN 13501 because Insulawool's raw material is inorganic basalt rock. Melting point is 1000 C.
- **Thermal conductivity:** Thermal conductivity value of the products used in buildings should be according to TS 825 h=0,040 W/mK.
- **It is produced in 2 different kinds; plain and one side fiberglass reinforced bituminous covered.**

Density (kg/m3)	150
Thickness (cm)	3 - 4 - 5
Dimension (cm) - (uncovered)	60x120
Dimension (cm) - (bituminous)	120x60
Compressive strength* (kg/m2)	3000

